

Technical Data Sheet

Hydroxypropyl MethylCellulose

HPMC K100M FG

1 Description

HPMC K100M FG is high viscosity Hydroxypropyl Methyl Cellulose (HPMC) which is designed for using in a wide range of food ingredient additives applications.

2 <u>Physical Analysis</u>

Appearance	:	White to slightly off-white fibrous or granular powder.
Identification A to E	:	Conform
Solution appearance	:	Conform
Methoxy	:	19.0-24.0%
Hydroxypropoxy	:	4.0-12.0%
Loss on drying	:	5.0% Max
Residue on ignition	:	1.5% Max
pН	:	5.0-8.0
Apparent viscosity	:	80000-120000cps
Particle size	:	Min. 98% pass through 100 mesh
<u>Heavy Metals</u>		
Heavy Metal	:	≤10ppm
Arsenic	:	≪3ppm
Lead	:	≪3ppm
Mercury	:	≤1ppm
Cadmium	:	≤lppm
<u>Micro bacteria</u>		
Total plate count	:	≪1000cfu/g
Yeast and Mould	:	≪100cfu/g
Coli form	:	Absent/g
Salmonella	:	Absent/g
Packaging		

5 <u>Packaging</u>

3

4

25kg fibre drum with inner liner.

6 <u>Regulation</u>

Meets all requirements of FCC,FSSC,E464 Hydroxypropyl Methyl Cellulose.

The information supplied is presented in good faith and has been derived from sources believed to be reliable. Since conditions of use are beyond our control, all risks are assumed by the user. No representation is expressed or implied, and nothing herein shall be construed as permission or recommendation to practice a patented invention without license.



Storage:

Store it in a cool, dry place below 30°C and protected against humidity and pressing, since the goods is thermoplastic, storage time should not exceed 36 months.

Safety notes:

The above data is in accordance with our knowledge, but don't absolve the clients carefully checking it all immediately on receipt. To avoid the different formulation and different raw materials, please do more testing before using it.

The information supplied is presented in good faith and has been derived from sources believed to be reliable. Since conditions of use are beyond our control, all risks are assumed by the user. No representation is expressed or implied, and nothing herein shall be construed as permission or recommendation to practice a patented invention without license.