KIMA CHEMICAL CO.LTD

Add:Zhangdian,Zibo, Shandong, P.R.China

Tel: +86-533-6281218

Email:sales@kimachemical.com

www.kimachemical.com



Technical Data Sheet

Hydroxypropyl MethylCellulose HPMC K200M

1 Description

HPMC K200M FG is high viscosity Hydroxypropyl Methyl Cellulose (HPMC) which is designed for using in a wide range of food ingredient additives applications.

2 Physical Analysis

Appearance White to slightly off-white fibrous :

or granular powder.

Identification A to E: ConformSolution appearance: ConformMethoxy: 19.0-24.0%Hydroxypropoxy: 4.0-12.0%Loss on drying: 5.0% MaxResidue on ignition: 1.5% MaxpH: 5.0-8.0

Apparent viscosity : 160000-240000cps

Particle size : Min. 98% pass through 100 mesh

3 Heavy Metals

Heavy Metal: ≤ 10 ppmArsenic: ≤ 3 ppmLead: ≤ 3 ppmMercury: ≤ 1 ppmCadmium: ≤ 1 ppm

4 Micro bacteria

5 Packaging

25kg fibre drum with inner liner.

6 Regulation

Meets all requirements of FCC,FSSC,E464 Hydroxypropyl Methyl Cellulose.

The information supplied is presented in good faith and has been derived from sources believed to be reliable. Since conditions of use are beyond our control, all risks are assumed by the user. No representation is expressed or implied, and nothing herein shall be construed as permission or recommendation to practice a patented invention without license.

KIMA CHEMICAL CO.LTD

Add:Zhangdian,Zibo, Shandong, P.R.China

Tel: +86-533-6281218

 ${\bf Email: sales@kimachemical.com}$

www.kimachemical.com



Storage:

Store it in a cool, dry place below 30°C and protected against humidity and pressing, since the goods is thermoplastic, storage time should not exceed 36 months.

Safety notes:

The above data is in accordance with our knowledge, but don't absolve the clients carefully checking it all immediately on receipt. To avoid the different formulation and different raw materials, please do more testing before using it.