

Technical Data Sheet

HPMC K200M

1 Description

HPMC K200M is high viscosity Hydroxypropyl Methyl Cellulose (HPMC) which is designed for using in a wide range of pharmaceutical excipient applications.

2 Physical Analysis

Appearance	:	White to slightly off-white fibrous or granular powder.
Identification A to E	:	Conform
Solution appearance	:	Conform
Methoxy	:	19.0-24.0%
Hydroxypropoxy	:	4.0-12.0%
Loss on drying	:	5.0% Max
Residue on ignition	:	1.5% Max
рН	:	5.0-8.0
Apparent viscosity	:	160000-240000cps
Particle size	:	Min. 98% pass through 100 mesh
Heavy Metals		
Heavy Metal	:	≤10ppm
Arsenic	:	≪3ppm
Lead	:	≪3ppm
Mercury	:	≤1ppm
Cadmium	:	≤1ppm
Micro bacteria		
Total plate count	:	\leq 1000cfu/g
Yeast and Mould	:	≪100cfu/g
Coli form	:	Absent/g
Salmonella	:	Absent/g

5 <u>Packaging</u>

3

4

25kg fibre drum with inner liner.

6 <u>Regulation</u>

Meets all requirements of USP, EP, JP, CP for the monograph Hydroxypropyl Methyl Cellulose 2208.

The information supplied is presented in good faith and has been derived from sources believed to be reliable. Since conditions of use are beyond our control, all risks are assumed by the user. No representation is expressed or implied, and nothing herein shall be construed as permission or recommendation to practice a patented invention without license.